

Product form	<i>Rolled plate</i>
Processing	<i>Band saw cutting, disc cutting</i>
Temper	<i>T3</i>
Density	<i>2,8 g/cm³ a 20°C</i>
Coefficient of thermal expansion	<i>22.9</i>
Modulus of elasticity	<i>75 N/mm2</i>
Hardness	<i>110 HB</i>
Melting range	<i>512-650</i>
Thermal conductivity (20°C)	<i>152 W/m° C (temper T0)</i>
Flexural fatigue strength	<i>3-5 kg/mm2 (temper H24)</i>

Good machinability

Moderate corrosion resistance

Poor weldability

Low drawability