

Product form	<i>Rolled plate</i>
Processing	<i>Band saw cutting, disc cutting</i>
Temper	<i>H111</i>
Density	<i>2,67 g/cm^3 a 20°C</i>
Coefficient of thermal expansion	<i>23.8</i>
Modulus of elasticity	<i>70000 N/mm2</i>
Hardness	<i>52 HB</i>
Melting range	<i>590-645</i>
Thermal conductivity (20°C)	<i>132 W/m° C (temper T0)</i>
Flexural fatigue strength	<i>3-5 kg/mm2 (temper H24)</i>

Fair machinability

Good formability

Excellent corrosion resistance

Good weldability